



Company Profile

Company Name	: Works & Building Co.
Factory	: Al-Qatami Insulation Material Factory
Factory Manager	: Eng. Mohamed F. Salem
Telephone (Head Office)	: 00 965 24814813/5/6/8 – 24961600 (100 Lines)
Fax	: 00 965 24812763
Telephone (Factory)	: 00 965 24766801 / 2 – 24738187
Fax	: 00 965 24718167
Address	: P.O.Box 415 Safat 13005 Kuwait
Email	: styroq@alqatami.com
Website	: www.styroq.com

Works&Building Co., is one of the oldest and well-established companies in Kuwait since 1952. Al-Qatami Insulation Material Factory was established in 1963 and it is one of the company's branches and one of the biggest factories in the Middle East for Insulation Materials.

The factory has presented its products in several international fairs. The products are manufactured from Expanded Polystyrene and Molded Injected Expanded Polystyrene with different densities.

Our Range of Products :

1. **STYROPANEL**® (Thermal Insulation with high physical specification)
2. **STYROWALL**® (EPS/PU Insulated Sandwich Panels)
3. **STYROFOAM**® (Extruded Polystyrene foam boards)
4. **STYROBOND, STYROFIX** (EIFS Exterior Insulation and Finish System)
5. **EPS Box outs for concrete.**
6. **EPS (Expanded Polystyrene) Rigid Pipe Insulation .**
7. **EPS (Expanded Polystyrene) Vegetable Boxes.**
8. **EPS (Expanded Polystyrene) Fish / Ice Boxes.**
9. **Insulated Sheets.**
11. **Custom Shapes.**
12. **Loose fill EPS/foam beads.**

غرفة تجارة وصناعة الكويت

شهادة تسجيل لعام

رقم الايصال: 160285470

2017

التاريخ: 2016/12/14

تشهد غرفة تجارة وصناعة الكويت أن

شركة الاشغال والبناء ذ.م.م

رقم السجل التجاري: 32438

رقم الترخيص التجاري: م/ 83/6241

تحت الرقم: 473

مسجل لديها منذ عام 1960

لزاولة: مكتب تجارة عامة ومقاولات ومواد البناء والمواد العازلة ومنزرة ومقهى ومطعم والعباب

وتسليية للأطفال ومنتجات المواد العازلة من الاسنروبور ومنتجاته ونتاج غرف التبريد

وقواطع معزولة وابواب خشبية لغرفة التبريد ونتاج البيوت الجاهزة الخشبية

والكرفانات والاثاث الخشبي بجميع انواعه***

التوقيع

22

وزارة التجارة والصناعة إدارة الشركات



اجازة شركة ممنوحة بموجب قانون التجارة رقم ٣ لسنة ١٩٦١
ومرسوم قانون الشركات رقم ١ لسنة ٢٠١٦ والقوانين المعدلة له
وقانون تراخيص المحلات التجارية رقم ١١١ لسنة ٢٠١٣

رقم الترخيص

١٩٨٣/٦٣٤١/م

تاريخ الاصدار

٢٠١٧/٠٩/٢٦

تاريخ الانتهاء

٢٠٢١/٠٩/٢٥

رقم الملف

٤٠٩٥ (م-م)

اسم الشركة و عنوانها :

شركة الاشغال والبناء / ذات مسؤولية محدودة

راس المال : ٣٠٧٣٠٠٠

الموقع : الشويخ الجديد
الشمارع : ملك / مجمع
الدولة : مكتب تجارة عامة ومقاولات
الافراض : القطعة :
المبني : ٥٠
الشقة / المحل : الميزانين

موافقة البلدية رقم

٢٨٧٣

التاريخ

١٩٨٣/٠١/١٩

رقم السجل التجاري

٣٣٤٣٨

التاريخ

١٩٨٣/٠١/٢٣

تنبيه

على المرخص له إشعار وزارة التجارة والصناعة عند هدم المحل او اخلائه او بيعه او تعديل نوع التجارة او اى تصرف اخر.

الملاحظات

١٩٨٣/٠١/١٩
٢٠٠٦/٠٣/١٢

١٩٨٣/٠١/١٩
٢٠٠٦/٠٣/١٢

بموجب عقد الشركة الموثق من كاتب العدل رقم ١/٣٨ جلد ١
وزارة العدل ٨١٤/جلد ١

حسان مرزوق مرضي الحارثي
مشرقة الخدمات التجارية
إدارة التراخيص التجارية

وكيل وزارة التجارة والصناعة

مدير إدارة الشركات

ر.م. ٤٠٣٦
طر. ٤٣٩٤



دولة الكويت



رقم الترخيص: ١٠٠٥٦
تاريخ الترخيص: ١٩٧١/٠١/٣١
تاريخ الانتهاء: ٢٠٢٣/٠٩/٢٧

الدولة: الكويت
الهيئة: الهيئة العامة للصناعة
الادارة: مركز الخدمة المتكاملة
المنطقة: جنوب السرة

ترخيص مشروع صناعي (منشأة صناعية) بدل فاقد

اسم صاحب/اصحاب التراخيص: شركة الاشغال والبناء
الرقم المدني: ٢٥٣٤٣٧٠
الكيان القانوني: كويتي (١٠٠%)
نسبة المساهمة: ذ.م.م

اسم المشروع الصناعي (الإسم التجاري):
مصنع القطامي للمواد العازلة فرع من شركة الاشغال والبناء

تاريخ السجل الصناعي: ٢٠٠٠/٠٢/٢٣

رقم السجل التجاري: ٣٢٤٣٨
رقم السجل الصناعي: ٢٧٣

isic code

المنتج

النشاط

٢٢٢.٣٣	صناعة لوازم العزل ومنع التسرب
--------	-------------------------------

المنتجات:-

المواد العازلة من الاستروبور ومنتجاته

الموقع

منطقة	قطعة	قسمة	الرقم الآلي	مالك القسمة
الشويخ الصناعية - ٢	الشويخ الجديد	٥٠	١٠٥٥٥٢٣٧	الهيئة العامة للصناعة

ملاحظة: على المرخص له الالتزام بالشروط الواردة خلف هذا الترخيص
تاريخ التنفيذ: ٢٠١٨-٠٩-٢٧

مدير الادارة

تعتبر هذه الرخصة نسخة الكترونية ولا تحتاج الى توقيع



0218092799407



طلب

تسجيل - إلغاء - تجديد

مفوض بالتوقيع

الهيئة العامة للقوى العاملة

إدارة عمل محافظة العاصمة

السيد / المدير العام للهيئة العامة للقوى العاملة

تحية طيبة وبعد

يرجي اعتماد / إلحاق توقيع السادة التالية ببياناتكم كمفوضين بالتوقيع على المعاملات الخاصة بالمنشأة

نموذج القتم
شركة الأشغال والبناء
WORKS & BUILDING CO.

اسم صاحب العمل : شركة الأشغال والبناء

الرقم المدني : 253437000000

الاسم التجاري : شركة الأشغال والبناء

نموذج التوقيع

اسم المفوض بالتوقيع : فيصل يوسف عيسى القطامي

الرقم المدني : 245010800031

نموذج التوقيع

اسم المفوض بالتوقيع : وليد يوسف عيسى القطامي

الرقم المدني : 251051101641

نموذج التوقيع

اسم المفوض بالتوقيع : قطامي يوسف عيسى القطامي

الرقم المدني : 256061700026

للاستعمال الرسمي

غرفة تجارة وصناعة الكويت
KUWAIT CHAMBER OF COMMERCE & INDUSTRY

تصديقه


تصديق

ملاحظة

على صحة التوقيع / التواقيع وصدقها

وتلحق التواقيع دون تحمل أدنى مسؤولية هنا تضمنه هذه الوثيقة

اسم الممثل : شركة الأشغال والبناء ق.م.م



رقم الفاتورة 170103722

التاريخ 28/03/2017

اسم الموظف وتوقيعه

Technical Data for EPS

Expanded polystyrene foam, also known as EPS foam, is made from a mixture of polystyrene and a gaseous blowing agent (generally pentane). Through the use of steam heat, the solid plastic is expanded into foam.

EPS foam offers a good strength, good first drop cushioning performance, and offers excellent insulation. The product is great for packing consumer electronics, hordy for the buildings, appliances, toys, food service items, and more. Below you will find technical data about our EPS foam products.

Technical Data for EPS Density 9-10 Kgm³:

- a) Thermal Conductivity : 0.042 W/ (M.K)
- b) Compressive stress : 40 Kpa
- c) Bending strength : 110 Kpa
- d) Type of the raw material : MS
- e) Particle Size : 1.24 - 1.66 (mm)

Remarks:

Attached the figures and tables regarding the properties, specifications and data from our supplier of the EPS raw-materials.

شركة الأشغال والبناء
WORKS & BUILDING CO.

Technical Data for EPS

Expanded polystyrene foam, also known as EPS foam, is made from a mixture of polystyrene and a gaseous blowing agent (generally pentane). Through the use of steam heat, the solid plastic is expanded into foam.

EPS foam offers a good strength, good first drop cushioning performance, and offers excellent insulation. The product is great for packing consumer electronics, appliances, toys, food service items, and more. Below you will find technical data about our EPS foam products.

Technical Data for EPS Density 12 to 14 Kg/m³:

- | | | |
|-------------------------|-----------------|----------|
| a) Thermal Conductivity | : 0.039 – 0.042 | W/ (M.K) |
| b) Compressive Strength | : 60 – 75 | (KPa) |
| c) Flexural Strength | : 69 | (Kpa) |
| d) Bending strength | : 195 – 230 | (Kpa) |
| e) Particle Size | : 0.81 – 1.1 | (mm) |

Remarks:

Attached the figures and tables regarding the properties, specifications and data from our supplier of the EPS raw-materials.

شركة الأشغال والبناء
WORKS & BUILDING CO.

Technical Data for EPS

Expanded polystyrene foam, also known as EPS foam, is made from a mixture of polystyrene and a gaseous blowing agent (generally pentane). Through the use of steam heat, the solid plastic is expanded into foam.

EPS foam offers a good strength, good first drop cushioning performance, and offers excellent insulation. The product is great for packing consumer electronics, appliances, toys, food service items, and more. Below you will find technical data about our EPS foam products.

Technical Data for EPS Density 16 to 18 Kg/m³:

- | | |
|-------------------------|---|
| a) Thermal Conductivity | : 0.036 – 0.038 W/ (M.K) |
| b) Thermal Resistance | : at (40 F = 0.74 K.m ² /W). |
| | At (110 F = 0.61 K.m ² /W). |
| c) Compressive Strength | : 90 – 110 (KN/m ²) |
| d) Flexural Strength | : 208 – 276 (Kpa) |
| e) Bending strength | : 195 – 230 (Kpa) |
| f) Particle Size | : 0.71 – 1.00 (mm) |

Remarks:

Attached the figures and tables regarding the properties, specifications and data from our supplier of the EPS raw-materials.

شركة الأشغال والبناء
WORKS & BUILDING CO.

Technical Data for EPS

Expanded polystyrene foam, also known as EPS foam, is made from a mixture of polystyrene and a gaseous blowing agent (generally pentane). Through the use of steam heat, the solid plastic is expanded into foam.

EPS foam offers a good strength, good first drop cushioning performance, and offers excellent insulation. The product is great for packing consumer electronics, appliances, toys, food service items, and more. Below you will find technical data about our EPS foam products.

Technical Data for EPS Density 24 -26 Kg/m³:

a) Thermal Conductivity	: 0.033 - 0.036	W/ (M.K)
b) Compressive strength	: 150 – 180	(Kpa)
c) Bending strength	: 330 – 350	(Kpa)
d) Particle Size	: 0.71 – 1.00	(mm)
e) Flexural strength	: 310 - 390	(Kpa)

Remarks:

Attached the figures and tables regarding the properties, specifications and data from our supplier of the EPS raw-materials.

شركة الأشغال والبناء
WORKS & BUILDING CO.

Expanded Polystyrene (EPS)

Technical Data Sheet

Expanded polystyrene foam, also known as EPS foam, is made from a mixture of polystyrene and a gaseous blowing agent (generally pentane). Through the use of steam heat, the solid plastic is expanded into foam.

EPS foam offers a good strength, good first drop cushioning performance, and offers excellent insulation. The product is great for packing consumer electronics, appliances, toys, food service items, and more. Below you will find technical data about our EPS foam products.

ASTM C 578 BS 3837 DIN 4102					
Physical Properties	Density (kg/M3)		18	20	24
	Thermal Resistance R-Value		(ASTM C518) R value per inch		
		40°F (5 °C)	4.17	4.25	4.55
		75°F (24 °C)	3.85	3.92	4.17
		110 F (44 °C)	3.45	4.3	4.65
	Thermal Conductivity K-Value		ASTM C165 at mean temp (24°c ±1) (K.m3/w)		
			0.0419	0.0394	0.0377
	Compressive strength @ 10% deformation, min		ASTM D1612 (Kpa)		
			90	90	104
	Flexural Strength		ASTM C203 (Kpa)		
173			208	242	
Dimensional Stability		change in dimension %			
		2	2	2	
Retarded Ignitability		According to DIN 53438			
		class K1 & K2			

شركة الأشغال والبناء
WORKS & BUILDING CO.

P.O.BOX: 415 Safat – 13005 Kuwait – Tel.: (+965) 24814813 /5/6/8 – 24961600 (100 Lines) – Fax: (+965) 24812763

Factory Tel.: 24766801/2 – 24738187 Fax: 24718167
Cable: KATAMI – C.R. 32438 - Email – styroq@alqatami.com